





DESCRIPTION: EVERSHIELD® Flat is an ultra-premium exterior, ultra-low VOC, 100% acrylic flat paint that provides maximum protection against UV color fade, mildew, efflorescence, water intrusion, and film failure (grain-cracking, peeling, blistering). **EVERSHIELD Flat** can be used on properly prepared and primed masonry, concrete, tilt-up, block, stucco, plaster, wood, and metal. Advanced technology and premium ingredients provide unparalleled performance, durability, coverage, and adhesion. Can be used down to surface and air temperature of 35°F.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne		SIN TYPE: 100% acrylic	SPECIAL INSTRUCTIONS		
FINISH (ASTM D 523): Flat: 2-4% on a 60° meter; 4-8% on an 85° meter			 CAUTION! Scraping or sanding surfaces of older buildings (especially pre- 1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N95 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety"or 		
COLORS: Stock colors: Swiss Coffee.					
TINT BASES: L Tintable White, M Medium, U Ultra Deep					
VISCOSITY@77°F/25°C (ASTM D 562): 102-110 KU					
			call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or /asbestos, or contact your state or local Health Agency.		
SOLIDS BY VOLUME (ASTM D 2697) 39.5% ± 2%		DLIDS BY WEIGHT 5.3% ± 2%	 This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before 		
WEIGHT PER GALLON (ASTM D 1475): 11.60 lbs.			painting.	and promote their growth. Contest any each contaitione before	
COMPOSITION BY WEIGHT Pigment-39.9% Vehicle-60.1% *Prime pigments 20.9 Acrylic resins 13.8 Reinforcing pigments 19.0 *Prime pigments include titanium dioxide (TiO ₂), plus all other pigments directly adding to the hiding power of this paint.			 This paint contains a preservative which inhibits the growth of mildew on surface of this paint film. When the air temperature is at 35°F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 35°F and at least 5°F above the dew point. Avoid using if rain or snow is expected within 2-3 hours, as in colder temperatures, it may require longer time before the paint film cures enough not to be affected by rain or snow. Do not apply at air or surface temperatures below 35°F or when air or surface temperatures may drop below 35°F within 48 hours. 		
RECOMMENDED FILM THICKNESS PER COAT Wet: 3.8 mils Dry: 1.5 mils					
PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS Approximately 350–400 sq. ft. per gallon, depending on surface conditions and			Standard latex primers cannot be used below 50°F. See the specific primer product information sheet for that product's application conditions.		
application techniques.			PRIMERS		
THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.			MASONRY Stucco: Tilt-up concrete:	SUPER-LOC [®] Premium (SLPR00) or	
AVERAGE DRY TIME@77°F/25°C (ASTM D 1640) To touch: 30–60 minutes Recoat: 2–4 hours Dry times and recoat times are temperature, humidity and film thickness dependent.			Poured-in-place: Plaster: Brick: Br		
APPLICATION EQUIPMENT: Brush, roller, airless spray			Concrete block:	Smooth BLOCFIL Premium (SBPR00) or	
PACKAGING: One-gallon, five-gallon containers			Smooth trowel:	SUPER-LOC [®] Premium (SLPR00)	
STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110°F for extended periods of time. Extreme temperatures may cause paint to become unusable. See <i>Paint Storage Best Practices</i> Technical Bulletin at dunnedwards.com for more information.			WOOD Trim, sash, fascia: Rough-sawn: T1-11 siding:	} EZ-PRIME [®] Premium (EZPR00)	
CLEANUP: Warm, soapy water			SYNTHETIC WOOD Masonite:	2	
DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. Do not mix with other products .			Hardboard: MDO siding:	ULTRA-GRIP [®] Premium (UGPR00)	
CONFORMS TO: ARB 2007 SCM & CALGreen 2016; MPI Approved Product #10; CRGI Green Wise Certified			METAL Ferrous:	BLOC-RUST [®] Premium (BRPR00) or ENDURAPRIME [™] Metal Primer (ENPR00)	
SAFETY DATA SHEET: Available at www.dunnedwards.com			Non-ferrous:	ULTRASHIELD [®] Galvanized Metal Primer (ULGM00) or	
SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.			Non Ichous.	BLOC-RUST [®] Premium (BRPR00)	
			Galvanized steel:	ULTRASHIELD [®] Galvanized Metal Primer (ULGM00) or *ULTRA-GRIP [®] Premium (UGPR00)	
			*for incidental use on galvanized **This product has been tested and certified by Coatings Research Group Inc., an international paint industry-organized ISO-accredited testing laboratory, to meet performance and environmental standards as shown on www.greenwisepaint.com. Dunn-Edwards is a member of CRGI.		



EVERSHIELD® Exterior

Flat Paint

EVSH10

PRODUCT INFORMATION

HEALTH & SAFETY CAUTIONS: INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N95 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Titanium Dioxide (13463-67-7); Copolymer Resin (Proprietary); Nepheline Syenite (37244-96-5); Feldspar (68476-25-5); Quartz (14808-60-7).

MARNING: Cancer and Reproductive Harm – www.P65Warnings.ca.gov